




KONGERIKET NORGE
The Kingdom of Norway

PCT/NO 99 000008

NO 99 / 8



Bekreftelse på patentsøknad nr
Certification of patent application no

1998 1118

► Det bekreftes herved at vedheftede dokument er nøyaktig utskrift/kopi av ovennevnte søknad, som opprinnelig inngitt 1998.03.13

► *It is hereby certified that the annexed document is a true copy of the above-mentioned application, as originally filed on 1998.03.13*

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)


1999.01.18

Freddy Strømmen

Freddy Strømmen
Seksjonsleder

Gro Halvorsen

Gro Halvorsen



PATENTSTYRET

Styret for det industrielle rettsvern

Til
Patentstyret
Boks 8160 Dep.
0033 Oslo

la - e

Utfyll s av Styret

Patentsøknad nr.

Inngivelsesdag

Alment tilgj ng lig

Behandl nde medl m

Int. Cl⁶

UR

COLC

Alm. tilgj.

14 SEPT. 1999

Søkers/fullmektigs referanse
(angis hvis ønsket):

P9815

13.mar98 617006

P981118 1

0,00

Oppfinnelsens
benevnelse:

"Katalysator"

Hvis søknaden er
en internasjonal søknad
som videreføres etter
patentlovens § 31:

Den internasjonale søknads nummer

Den internasjonale søknads inngivelsesdag

Søker:

Navn, bopel og adresse.
(Hvis patent søkes av flere.
Opplysning om hvem som skal
være bemyndiget til å motta
meddelelser fra Styret på vegne
av søkerne).

(Fortsett om nødvendig på neste side)

Norsk Hydro ASA

0240 Oslo

Oppfinner:

Navn og (privat-) adresse.

(Fortsett om nødvendig på neste side)

Terje Fuglerud
Snarveien 1
3925 Porsgrunn

Per Torbjørn Skaugset
Borgeåsen Terrasse 15
3911 Porsgrunn

Fullmektig:

Hvis søknad tidligere
er inngitt i eller
utenfor riket:

(Fortsett om nødvendig på neste side)

Venche Høines Johnsen, Norsk Hydro ASA, 0240 Oslo

Prioritet kreves fra dato..... sted nr.

Prioritet kreves fra dato..... sted nr.

Prioritet kreves fra dato..... sted nr.

Prioritet kreves fra dato..... sted nr.

Hvis avdelt søknad:

Den opprinnelige søknads nr.:.....og dennes inngivelsesdag

Hvis utskilt søknad:

Den opprinnelige søknads nr.:..... begjært inngivelsesdag

981118

Angivelse av tegnings-
figur som ønskes
publisert sammen med
sammendraget

Fig. nr.

POSTADRESSE
Boks 8160 Dep.
0033 Oslo

KONTORADRESSE
Københavngt. 10
Oslo

TELEFON
22 38 73 00

TELEKS
19 152
nopat n

TELEFAKS
22 38 73 01

POSTGIRO
0808 5170709

BANKGIRO
1600.40.39916

13.MAR98 981110

The present invention relates to a catalyst for the synthesis of ammonia from hydrogen and nitrogen.

The ammonia synthesis catalyst play an important role in the manufacture of ammonia. It effects both the economics and operating conditions of ammonia plants.

Industrial catalysts for ammonia synthesis must satisfy a number of requirements: high catalyst activity at the lowest possible reaction temperatures in order to take advantage of the favourable thermodynamic equilibrium at low temperatures, good resistance to poisoning by oxygen-, chlorine- and sulphur -containing compounds, long life and high mechanical strength.

In order to save energy the synthesis pressure has been steadily reduced from 250-350 bar to 80-150 bar during the last 30 years due to optimised operation of the synthesis loop made possible by new technology, especially for fabrication of the converter. Improvements in the front end has drastically reduced the content of catalyst poisons (oxygen-, sulphur- and chlorine-containing compounds) in the gas inlet to the converter. However, the drop in synthesis pressure necessitates a three- to four-fold increase in the catalyst volume. The demands upon the catalyst quality has also increased. Apparently small improvements in the catalyst activity may lead to major improvements of the operation of a modern ammonia synthesis loop.

The ammonia synthesis catalyst precursor, the unreduced catalyst, is manufactured by melting iron oxides, mainly magnetite, and oxides or carbonates of Al, K, Ca and Mg, the so-called promoters. The melting is performed in electrical furnaces at a temperature of above 1600 °C. The ratio $\text{Fe}^{2+}/\text{Fe}^{3+}$ in the melt is normally in the range 0.5-0.75. The melt is then poured into metal trays where it solidifies and cools. The

solid precursor is then broken up, crushed and sieved to obtain the required grain size.

The precursor is reduced to active iron catalyst "in situ" in the ammonia synthesis converter or used to manufacture the prereduced catalyst by a complete reduction under optimised conditions in a prereduction reactor. This material is pyroforic, but after a skin oxidation of the active surface with oxygen, it can be handled safely in air at ambient temperatures.

The promoters mentioned above, containing Al, K, Ca and Mg, are essential for the formation of a large surface of iron in the reduced catalyst and for the kinetics of ammonia formation.

Since the development of the catalyst started, about 90 years ago, the concentration of these promoters have been optimised to obtain maximum activity and to meet the additional requirement mentioned above. Further improvements seem only possible by adding new promoters, or new combination of promoters.

Cobalt oxide has been used as such a new promoter.

From US patent 3839229 it is known an ammonia synthesis catalyst where cobalt oxide is used as a promoter. The catalyst consists essentially of a solid solution of iron oxide and cobalt oxide and said cobalt oxide is present in an amount of 5 to 10 percent by weight expressed as cobalt. In the catalyst there is further included a promoter selected from the group consisting of alumina, silica, zirconia, magnesia, lime (CaO), potassium oxide and rare earth metal oxides.

Another possible promoter is titanium oxide. Only few catalysts using this promoter have been previously described. S.A. Abdukadyrova et al. have in "Tr.Mosk.Khim.-Tekhnol.Inst. (1970), No.2, 122-5", described that titanium oxide improves the thermal resistance but reduces the activity.

Titanium oxide used as a structural promoter is described by M. E. Dry et al in "Journal of Catalysis", 6, page:194-199, 1966. Titanium oxide is not so effective as aluminium oxide with regard to surface area. This area and the volume of

chemisorbed CO normally increase with promoter content, but in contrast to the other promoters (Al_2O_3 , MgO , CaO) TiO_2 had a maximum in the volume of chemisorbed CO at about 0.5 g atom cation per 100 g atom Fe.

The main object of the present invention was to develop a catalyst for ammonia synthesis with improved activity.

Higher activity could be utilized in two ways: High reaction rate at high ammonia concentrations or higher activity at low temperatures.

The catalyst activity may be expressed as a rate constant in a rate equation for the synthesis reaction. The rate is a function of temperature, pressure and the composition of the gas, and decreases rapidly with increasing ammonia concentrations. Thus a large fraction of the catalyst volume in a synthesis converter will have ammonia concentration approaching the exit concentration. Hence, to improve the efficiency, increasing the reaction rate at high ammonia concentration is of particular interest.

As the equilibrium temperature decreases with increasing ammonia concentration, searching higher conversion by increasing the reaction rate at high ammonia concentration also means searching a catalyst with higher activity at low temperature.

The inventors have manufactured a lot of samples of iron oxide based catalysts with various promoters in various concentrations to improve the catalyst activity. In addition to the conventional promoters mentioned above, new promoters have been tested, in particular cobalt- and titanium oxide.

The inventors found that the reaction rate at high ammonia concentration increased with 10-20% when both cobalt- and titanium oxide were used as promoters together with the conventional promoters.

The most preferred catalyst was achieved when the concentration of cobalt was between 0.1% and 3.0 % by weight of metal and when the concentration of titanium was between 0.1 % and 1.0 % by weight of metal.

The atomic ratio $\text{Fe}^{2+}/\text{Fe}^{3+}$ was between 0.5-0.65.

The present invention will thus in its widest scope comprise a catalyst for the synthesis of ammonia from hydrogen and nitrogen consisting of iron oxides and promoters where the promoters comprise oxides of both cobalt and titanium in addition to Al, K, Ca and Mg oxides.

The invention will be further explained in the example.

Example:

Samples were made by mixing iron ore, mainly magnetite, Fe_3O_4 , with promoters. These mixtures were then melted in a ceramic crucible in a laboratory furnace. The temperature was kept at about 1600 °C. The ratio of $\text{Fe}^{2+}/\text{Fe}^{3+}$ was adjusted to within 0.5 to 0.65 by adding Fe-metal to the melt.

The melt was then poured into an iron crucible and cooled.

The concentration of the promoters in the samples varied as shown in table I:

Table I:

K	0.4 - 0.5
Ca	1.6 - 1.8
Mg	0.3 - 0.5
Al	1.5 - 1.8
Co	0.10- 3.00
Ti	0.14- 0.95

The balance being iron oxides with natural impurities. The cooled samples were crushed and sieved to 0.4 - 0.63 mm particles for testing in a microreactor.

Table II:

Sample	Co w %	Ti w %	Average Relative Catalyst Activity at 350°C	Relative Reaction Rate (20% NH ₃ and 420°C)	Average Relative Catalyst Activity at 420°C
1 (reference)	0	0.14 (impurity)	1.0	1.0	1.0
2	1.38	0.14 "	1.0	1.06	1.06
3	2.94	0.14 "	1.04	1.08	1.13
4	0.1	0.83	0.91	0.86	0.91
5	0.1	0.4	0.71	0.97	0.93
6	0.1	0.91	1.04	0.91	1.02
7	1.24	0.41	1.08	1.13	1.18
8	0.35	0.38	1.04	1.22	1.13
9	0.56	0.54	1.12	1.22	1.17

Table II shows that the relative reaction rate was highest at high concentration of ammonia (20%) when both cobalt oxide and titanium oxide were added as promoters (compare sample 7-9 with sample 1).

Furthermore, the table II shows that by adding either cobalt oxide or titanium oxide alone, together with the other conventional promoters, a lower relative reaction rate at high concentration of ammonia was obtained (compare samples 2-3 and 4-6 with sample 1).

Furthermore, table II shows that the activity was increased at temperatures down to 350°C when both cobalt- and titanium oxide were added as extra promoters (see sample 7-9).

The example also shows that the activity was increased both at low and high reaction temperature when both cobalt- and titanium oxide were added as promoters.

CLAIMS:

1. A catalyst for the synthesis of ammonia from hydrogen and nitrogen consisting of iron oxides and promoters characterised in that the promoters comprise oxides of both cobalt and titanium in addition to Al, K, Ca and Mg oxides.
2. A catalyst for the synthesis of ammonia from hydrogen and nitrogen according to claim 1, characterised in that, the concentration of cobalt is between 0.1% and 3.0 % by weight of metal and the concentration of titanium is between 0.1% and 1.0% by weight of metal.



Abstracts

The present invention relates to a catalyst for the synthesis of ammonia from hydrogen and nitrogen consisting of iron oxides and promoters where the promoters comprise oxides of both cobalt and titanium in addition to Al, K, Ca and Mg oxides, and where the concentration of cobalt is between 0.1% and 3.0 % by weight of metal and the concentration of titanium is between 0.1% and 1.0% by weight of metal.

